




**FLUROBOND™**  
HIGH DEFINITION COATINGS




Regal White\*  
IR = .68  
IE = .89



Bone White\*  
IR = .65  
IE = .90



Stone White\*  
IR = .62  
IE = .90



Almond\*  
IR = .57  
IE = .90



Sandstone\*  
IR = .51  
IE = .89



Surrey Beige\*  
IR = .41  
IE = .90



Sierra Tan\*  
IR = .38  
IE = .90



Slate Gray  
IR = .22  
IE = .91



Musket Gray  
IR = .15  
IE = .90



Medium Bronze  
IR = .10  
IE = .90



Mansard Brown  
IR = .08  
IE = .93



Dark Bronze  
IR = .07  
IE = .90



Old Town Gray\*  
IR = .25  
IE = .90



Hemlock Green  
IR = .21  
IE = .90



Patina Green\*  
IR = .26  
IE = .89



Teal  
IR = .13  
IE = .88



Classic Green  
IR = .14  
IE = .90



Hartford Green  
IR = .09  
IE = .90



Charcoal Gray  
IR = .10  
IE = .90



Matte Black  
IR = .07  
IE = .89



Slate Blue  
IR = .22  
IE = .89



Regal Blue  
IR = .16  
IE = .88



Apothecary Blue\*<sup>P</sup>  
IR = .26  
IE = .85



Burgundy\*  
IR = .25  
IE = .90



Colonial Red  
IR = .23  
IE = .92



Terra Cotta\*  
IR = .38  
IE = .89



Banner Red\*<sup>P</sup>  
IR = .48  
IE = .89



Pewter<sup>P</sup>  
IR = .23  
IE = .87



Bright Silver\*<sup>P</sup>  
IR = .57  
IE = .77



Bright Copper\*<sup>P</sup>  
IR = .45  
IE = .86



\* = Energy Star Approved for steep slope applications  
IR = Initial Reflectivity  
IE = Initial Emissivity  
P = Subject to premium pricing

# Flat Sheet Color Availability

	Steel				Aluminum				
	26ga LG	24ga	24ga LG	22ga	18ga	.032"	.040"	.050"	.063"
<b>PVDF</b>									
Regal White		•	•	•	•	•			•
Bone White		•		•		•		•	
Stone White		•	•			•	•	•	
Almond		•	•			•	•	•	
Sandstone		•	•	•		•	•	•	
Surrey Beige		•		•		•	•	•	
Sierra Tan		•	•			•	•	•	
Slate Gray	•	•	•	•		•	•		
Musket Gray		•				•			
Medium Bronze		•	•			•	•	•	
Mansard Brown		•				•	•	•	
Dark Bronze	•	•		•	•	•	•	•	•
Old Town Gray		•	•			•			
Hemlock Green		•				•			
Patina Green		•	•			•			
Teal		•	•			•			
Classic Green	•	•	•			•	•		
Hartford Green	•	•				•			
Charcoal Gray	•	•				•			
Matte Black	•	•				•	•		
Slate Blue	•	•				•			
Regal Blue		•	•			•			
Apothecary Blue +		•				•		•	
Burgundy		•				•			
Colonial Red	•	•				•			
Terra Cotta		•	•			•			
Banner Red +		•				•			
<b>PVDF MICA</b>									
Pewter +		•				•			
Bright Silver +		•				•	•		
Bright Copper +		•				•			
<b>POLYESTER</b>									
White/White						•			
Dark Bronze/White						•			
Matte Black/White						•	•		
<b>000250" ANODIZED</b>									
Clear						•	•	•	
Dark Bronze							•		

**Notes on availability:**

- 26ga. is 40.25" in width, 24ga, .032", .040", .050" & .063" are standard 48.25" in width, 22ga & 18ga are 44.375" in width for painted items.
- Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
- Protective strippable film is available upon request.
- Apothecary Blue, Banner Red, Pewter, Bright Copper and Bright Silver are subject to premium pricing.
- LG = Low Gloss.
- Subject to change without notice.

Paint Performance Properties	Hot Dipped Galvanized Steel or Galvalume	Aluminum
<b>Accelerated Weathering</b> ASTM D 4587 (Drew Cycle Weatherometer)	Hours: 3,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max
ASTM G 23	Hours: 5,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max	Hours: 5,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max
<b>Salt Spray</b> ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/16" (1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
<b>Humidity</b> ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters	Hours: 3,000 Total Rating: 10, no blisters
<b>Formability</b> ASTM D 4145	2T	2T
<b>ASTM D 522</b> (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
<b>Pencil Hardness</b> ASTM D 3363	HB-2H	HB-2H
<b>Abrasion Resistance</b> ASTM D 968	50-80 Liters of falling sand	50-80 Liters of falling sand
<b>Specular Gloss</b> ASTM D 523	20-35 at 60 °	20-35 at 60 °
<b>Reverse Impact</b> ASTM D 2794	3 x Metal thickness in inch-lbs. No loss of adhesion	1 1/2 x Metal thickness in inch-lbs. No loss of adhesion
<b>Flame Test</b> ASTM E 84	Class A rated coating	Class A rating coating



a Euramax company

**Georgia Facility**  
308 Alabama Blvd.  
Jackson, GA 30233  
800-884-4484  
Fax 770-775-6167

**Texas Facility**  
404 E. Dallas Rd.  
Grapevine, TX 76051  
800-477-9066  
Fax 817-488-0466

**Salem Facility**  
4570 Ridge Dr.  
Salem, OR 97303  
800-477-8028  
Fax 503-393-5813

**Corporate Office**  
3449 Hempland Rd.  
Lancaster, PA 17601  
800-477-2741  
Fax 717-397-1040

www.fabral.com

Fabral's standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply. Consult www.fabral.com for additional information.

